

# ARDROX<sup>®</sup> AV 25

**Penetrating and water displacing, all purpose corrosion inhibiting compound; leaving soft, waxy film**

## PRIMARY APPLICATION

ARDROX<sup>®</sup> AV 25 can be used in all areas of the airframe. It is designed for treatment of areas where a soft, lubricating film is required, i.e. pulleys, control cables, and other moveable parts. ARDROX AV 25 is used for protection of all, commonly used aerospace metals and alloys.

## CHEMICAL CHARACTERISTICS

composition.....	aliphatic hydrocarbon with 0.5% aromatics max.
appearance.....	transparent
physical form.....	liquid
flash point.....	40°C
bulk density.....	6.84 lbs/gal
viscosity.....	40 sec.

## APPLICATION PROCEDURE

ARDROX AV 25 can be applied by brushing, but preferably spraying. It can be sprayed using the ARDROX ACS SYSTEM, or the ARDROX AAS SYSTEM (airless application). Recommended dry film thickness is 25 microns (1mil). Product should be applied to a wet film thickness of approximately 50 microns (2 mils) to allow for solvent evaporation.

## APPROVALS

### Meets or exceeds:

AIRBUS INDUSTRIE TN 007.10138, Type I, Grade 2 AMS 3066  
 BOEING BMS 3-26, Type I  
 MC DONNELL DOUGLAS DMS 2150  
 MIL-C-16173 D, Grade 3  
 SAAB AIRCRAFT STD 161454

### Approved by:

AIRBUS INDUSTRIE  
 GULFSTREAM AEROSPACE  
 MCDONNELL DOUGLAS  
 SAAB AIRCRAFT

## SAFETY AND HANDLING

Prior to handling and use of any of the material referenced in this document, the Material Safety Data Sheets should be read and understood by all personnel in contact with these materials.

## KEEP OUT OF REACH OF CHILDREN

## STORAGE

Dry indoor storage at temperatures between 4°C - 38°C is recommended, away from any incompatible materials referenced in Material Safety Data Sheets. All containers should be kept tightly closed when not in use.

## SHELF LIFE

The shelf life is 3 years.

## DISPOSAL

Any disposal of the materials referenced in this document should be in accordance with all applicable federal, state, and local regulations. The process solution can contain components other than those present in the materials as supplied. Analysis of process solutions may be required prior to disposal.

Oakite Products, Inc. warrants that the product or products described herein will conform with its published specifications. The products supplied by Oakite and information related to them are intended for use by buyers having necessary industrial skill and knowledge. Buyers should undertake sufficient verification and testing to determine the suitability of the Oakite materials for their own particular purpose. Since buyer's conditions of use of products are beyond Oakite's control, Oakite does not warrant any recommendations and information for the use of such products. OAKITE DISCLAIMS ALL OTHER WARRANTIES INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH THE USE OF ITS PRODUCTS.

**Chemetall**  
**Oakite**



ISO 9001:2000  
FM 93653

---

**Corporate Headquarters and Eastern Branch (800) 526-4473 • Central Branch (Midwest) (877) 941-3800**  
**Western Branch (800) 331-1197 • Oakite Canada Limited (800) 668-4318**  
**Chemetall Mexicana 011 52 55 5656 1490 • Chemetall do Brasil Ltda. (5511) 4066 8800**  
**Website: [www.oakite.com](http://www.oakite.com) • E-mail: [oakite.products@chemetall.com](mailto:oakite.products@chemetall.com) • Shop online at [www.oakitestore.com](http://www.oakitestore.com)**

F16981-R 05/2006  
Printed in the USA